Resistance table

BUSCHJOST Solenoid Valves

Which materials for which fluids?

The resistance table supports you in your search for suitable materials and compiles information on the chemical resistance of sealing and enclosure materials for gaseous and liquid media. **The table is subject to updating.

Contents of the resistance table

- The suitability of the materials is confirmed by a simple "+".
- For some media, only the minimum requirement is confirmed with a "+". This means that higher quality materials can also be used.
- Ask if you are unsure, even if a medium is not listed.
- Operating conditions cannot be derived from the table.
- There is no such thing as an unconditional application. Therefore, also consider operational dependencies such as pressure, temperature, viscosity, concentration, degree of contamination. These can have a negative effect on the longevity of the valve.
- The table does not claim to be complete.
- No warranty claims can be derived from the information given.
- We reserve the right to change the information given at any time without notice.

Technical hotline Germany +49 5731 18660 99

			Material Sealing																						Material Housing															
Media	Density (kg/m³)	Gaseous	EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polytetrafluoroethylene
potassium hydroxide KOH, 20%, aqueous 20°C	1000		+																	+						+	+													
potassium hydroxide KOH, 50%, aqueous 60°C	1000																			+						+	+													
2-methylpentan, isohexane, liquid																				+	+				+	+	+								+					
Acetic acid, 50% CH3COOH	1005																			+							+													+
Acetone CH3COCH3	791		+														+			+	+				+		+				+			+	+	+	+			
Acetylene C2H2	1.17	ja	+														+			+					+		+				+				+	+	+			
Adblue	1087						+													+					+	+	+													
Additives for Fuels							+													+	+				+	+	+								+					
Air	1.2	ja	+	+	+		+					+					+		+	+	+	+		+	+	+	+				+		+	+	+	+	+	+	+	
Ammoniac NH3	0.77	ja	+		+												+			+					+	+	+										+			
Antifrogen N	1140																			+															+					
Argon Ar	1.78	ja					+					+					+			+		+			+		+				+			+	+		+			
Argon, liquified cryogenic -186°C														+						+					+		+		+						+					
Bilge Water (water-oil mix)	1000		+				+					+								+	+						+								+	+	+			
Biodiesel, Rapsmethylester (RME)	885						+													+					+	+	+													
biogas (wet, max. 3% H2S)		ja					+																			+														
Biogas <= 0,5% H2S		ja					+					+					+			+	+				+		+				+					+		+		
Brake Fluid	1100		+	+																+						+	+							+	+		+			
Butadien C4H6	2.4	ja																		+						+	+													

			Material Sealing																						Material Housing															
Media	Density (kg/m^3)	Gaseous	EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polyetrafluoroethylene
Calibration gas, test gas, dry	0.72	ja					+										+			+	+				+						+									
chlorine gas, dry Cl2																				+	+						+													
CNG - Compressed Natural Gas	0.7	ja								+		+		+			+			+					+		+		+		+				+					
CO carbon monoxide	1.25	ja					+					+					+			+	+				+		+				+			+	+	+	+			
CO2 carbon dioxide gas	1.98	ja					+			+		+					+			+	+	+			+		+		+		+			+	+	+	+			
Coke oven gas	0.6	ja					+																			+	+								+					
Condensate			+				+													+					+		+							+	+	+	+	+		
Condensate 200°C																				+	+					+	+							+	+	+	+	+		
Cool Emulsion, Cooling Water	1000		+				+	+				+					+			+	+				+	+	+							+	+	+	+			
Dimethylether DME	2	ja																		+	+				+	+	+													
Dipropylenglycolmethylether DPM																				+	+				+		+													
dirty Fluids							+						+								+				+		+							+	+					
Eisen-(II)-Chlorid (Ferrochlorid) FeCl3 - Lösung	1000		+																																					
Ethane C2H6	1.36	ja					+					+					+			+					+		+				+			+	+					
Ethanol	789		+		+												+			+	+				+	+	+							+	+	+	+			
Ethylacetat CH3 CO2 CH2 CH3	894																			+	+					+	+							+	+	+	+			
Ethylene C2H4	1.26	ja					+					+								+		+			+									+	+					
Ethylene glycol C2H6O2 50%	1000		+																							+														
flour, powder, dust, soot			+				+					+																		+			+							
Flue Gas SOX, SO2, N2, O2, CO		ja													+		+			+						+	+													
Formic Acid HCOOH 50% 20°C	1000																			+						+	+													
Forming Gas		ja					+					+								+	+	+					+								+	+	+			
Fuel Oil	920						+										+			+	+				+		+							+	+	+	+			
gaseous, liquid, aggressive		ja													+					+						+	+										+			
Gases flammable		ja					+					+					+			+					+		+				+			+	+	+	+			

			Material Sealing																						Material Housing															
Media	Density (kg/m^3)	Gaseous	EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polytetrafluoroethylene
Gasoline, Dieseloil, Fuels	800						+													+	+					+	+							+	+	+	+	+		
Glycerine aqueous, H2O with C3H8O3	1260						+														+				+															
granules, sand, gravel, chalk			+				+					+																		+			+							
Grinding oil with dirt and abrasion particles							+														+				+															
HCL Hydrogen chloride gas	1.64	ja					+													+	+						+													
Helium Gas He	0.18	ja					+			+		+					+			+					+	+	+		+		+				+					
heptane (hexan, petrol)	684						+					+								+	+				+	+	+								+					
high viscous Fluids up to 1000 mm^2/s							+														+				+		+								+					
Hot Air 180°C	1.2	ja																		+	+					+	+							+	+	+	+	+		
hot Gases 230°C	1	ja													+											+	+								+		+			
Hydraulic Oil	800						+					+					+			+		+			+		+							+	+	+	+			
Hydrogen H2	0.09	ja					+			+						+	+			+	+				+	+	+		+			+			+		+		+	
Hydrogen Peroxide 0,5% H2O2, +20°C	1000						+													+						+	+													
Hydrogen Sulfide, gas, dry, H2S	1.6	ja	+				+													+	+				+	+	+													+
Isobutane C4H10	2.51	ja					+													+	+				+		+								+					
isoprene C5H8	681																			+	+				+	+	+													
Isopropanol CH3 CH(OH)CH3	786						+													+	+				+	+	+							+	+					
JP-8 jet fuel aviation, kerosine	800						+										+			+	+				+	+	+								+		+			
Liqud Nitrogen -196°C LN2														+						+					+		+		+						+					
Liquid Carbon Dioxide LCO2							+													+	+				+		+		+						+					
LNG liquified natural gas -162°C	1590													+						+							+		+						+					
LPG liquified petrol gas propane, butane	600						+													+	+				+	+	+							+	+		+	+	+	
Lubricant, gear oil CLP460	900						+														+														+					
Mercaptane		ja				+											+			+	+				+	+	+				+									
Methane CH4	0.72	ja					+					+					+			+		+			+	+	+				+			+	+	+	+	+		
Methanol Alcohole CH3OH	793		+		+												+			+					+	+	+													

Media	Density (kg/m³)	Gaseous	Material Sealing																					
			EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C
Mineral Oil	800						+					+					+			+				
Motor Oil	800						+					+					+			+	+			
natural Gas CH_4	0.7	ja					+			+		+		+			+			+	+	+		
neongas NE	0.84	ja					+					+												
Nitric acid aqueous 40%, HNO_3	1100						+													+	+			
Nitrogen dioxide NO_2	2.053																			+				
Nitrogen Gas N_2	1.25	ja	+				+			+		+					+		+	+	+	+		
Nitrogen oxides, nitrous gases NO_x		ja															+			+				
Nitrous Oxide N_2O	2	ja					+			+							+			+	+			
Odorant		ja				+											+			+				
Oxygen Liquid, -183°C LOX	1140																			+				
Oxygen O_2	1.43	ja					+										+			+	+			
paint, ink - highly viscous			+				+					+									+			
Phenol, Carbolic Acid - diluted with water						+														+				
Propane/Butane gaseous C_3H_8	2	ja					+					+					+			+	+			
Propionic acid $C_3H_6O_2$	990						+													+	+			
propylene glycol $C_3H_8O_2$							+					+								+				
Propylene, Propene - C_3H_6	1.915	ja					+													+				
Rape Oil							+													+				
refrigerant R290, R600a																				+	+			
Refrigerant R407C	2.51	ja																		+	+			
Resins							+													+	+			
sea water	1000																							
sewage gas, proportionally H_2S, NH_3	0.77	ja	+																					
silan gas	1.34	ja					+													+	+			
slurry of chalk							+																	

Media	Material Housing															
	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polyetrafluoroethylene
Mineral Oil	+	+	+							+	+	+	+			
Motor Oil	+	+	+							+	+	+	+			
natural Gas CH_4	+	+	+		+		+			+	+	+	+	+	+	
neongas NE											+					
Nitric acid aqueous 40%, HNO_3		+	+													+
Nitrogen dioxide NO_2	+	+	+													
Nitrogen Gas N_2	+	+	+		+		+		+	+	+	+	+			
Nitrogen oxides, nitrous gases NO_x	+	+	+													
Nitrous Oxide N_2O	+		+		+		+				+		+			
Odorant	+		+				+									
Oxygen Liquid, -183°C LOX			+		+						+					
Oxygen O_2	+	+	+				+			+	+	+	+	+		
paint, ink - highly viscous						+			+		+					
Phenol, Carbolic Acid - diluted with water		+	+													
Propane/Butane gaseous C_3H_8	+	+	+				+			+	+	+	+	+	+	
Propionic acid $C_3H_6O_2$	+	+	+													
propylene glycol $C_3H_8O_2$										+	+	+				
Propylene, Propene - C_3H_6	+	+	+							+	+					
Rape Oil			+							+	+	+	+			
refrigerant R290, R600a	+	+	+							+	+					
Refrigerant R407C	+	+	+							+	+					
Resins	+	+	+													
sea water																
sewage gas, proportionally H_2S, NH_3			+													
silan gas	+	+	+													
slurry of chalk	+										+					

			Material Sealing																						Material Housing															
Media	Density (kg/m³)	Gaseous	EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polytetrafluoroethylene
Sodium hydroxide (sodium hydroxide), NaOH, 30%, +20°C			+																	+						+	+													
sodium hypochlorite NaOCl (Chlorine bleach) max. 12%, +20°C																				+							+													
Sodium nitrite - aqueous NaNO2	1290						+					+								+					+	+	+													
Sodium Phosphate NA3PO4							+										+			+	+				+	+	+				+									
sodium silicate (waterglass)	1000						+					+								+	+				+	+	+													
Sole (cooling sole) up to 40%			+									+																							+					
Steam 110°C	0.6		+																	+					+	+	+							+	+	+	+	+		
Steam 180°C	0.6	ja																		+	+					+	+							+	+	+	+	+		
Steam 200°C																				+	+					+	+							+	+		+			
Steam 230°C															+											+	+								+		+			
Steam 250°C									+		+				+											+	+								+		+			
Steam 300°C									+		+															+	+										+			
Sulfur Dioxide Gaseous, dry SO2	2.93	ja																		+	+				+	+	+													
Sulfur Dioxide Gaseous, wet, SO2	2.93	ja																		+							+													
Sulfur Dioxide Liquid SO2																				+	+				+	+	+													
Sulfuric acid H2SO4 max. 10%, 20°C	1.6	ja					+																				+													
Tetraflourmethane CF4, gas	1.69	ja																		+	+				+		+													
Thermal-Oil >180°C	1000																			+	+					+	+							+	+	+	+	+		
Thermal-Oil >200°C	1000																			+							+								+		+			
Thermal-Oil >230°C	1000														+											+	+								+		+			
Thermal-Oil >250°C	1000								+		+				+											+	+								+		+			
Thermal-Oil >300°C	1000										+																+										+			
Toluol C6H5CH3	867																			+	+				+		+								+					
Triglycole, Triethylenglycole C6H14O4	1100						+													+						+	+													
Urea	1300						+													+						+	+													

Material Sealing

Media	Density (kg/m^3)	Gaseous	EPDM -30°C 140°C	EPDM/EPDM -30°C 140°C	EPDM/PTFE -30°C 120°C	FFKM -15°C 200°C	FKM -10°C 140°C	FKM/FKM -10°C 120°C	Metall -40°C 300°C	Metall/HP -40°C 80°C	Metall/Wills® -20°C 400°C	NBR -10°C 80°C	NBR/NBR -10°C 80°C	PCTFE -200°C 80°C	PEEK-HT -40°C 250°C	Peek/PCTFE -40°C 80°C	PEEK/PCTFE-HP -196°C 140°C	PEEK/UHMW-PE	POM -10°C 90°C	PTFE -196°C 230°C	PTFE/FKM -20°C 150°C	PTFE/NBR -20°C 80°C	PTFE/Peek -10°C 80°C	PTFE/Silikon -40°C 230°C
Vacuum	1.2	ja	+	+			+	+				+	+											
Vacuum + Pressure		ja	+	+				+				+	+							+				
vapour aggressive (natural gas + steam)	0.9	ja				+														+				
Water demineralised, Osmose	1000		+				+													+	+			
Water H2O with Glycole	1000		+				+	+				+					+			+	+			
Water, H2O	1000		+		+		+	+				+	+				+			+	+	+	+	
Water, Hot above 90°C H2O	1000		+				+	+												+	+			

Material Housing

Media	AISI 304 - 1.4301 -196°C 250°C	AISI 316 -196°C 300°C	AISI 316 Ti -196°C 300°C	AISI 316 Ti - 1.4571(81) -20°C 160°C	AISI 316L - 1.4404 -196°C 80°C	AISI 316L - 1.4435 -40°C 250°C	AISI 318LN - 1.4462 -40°C 250°C	AISI S165M - 1.4418 -40°C 80°C	aluminium AL anodised	CC499K red brass -40°C 200°C	CW617N brass -196°C 300°C	EN-GJL250 grey cast -10°C 300°C	EN-GP240GH cast steel -20°C 300°C	EN-JS1025 ductile iron -10°C 300°C	P250GH+N - C22.8 PN160 -10°C 300°C	PTFE Polyetrafluoroethylene
Vacuum		+	+							+	+	+	+			
Vacuum + Pressure		+	+							+	+	+	+			
vapour aggressive (natural gas + steam)		+	+													
Water demineralised, Osmose	+	+	+								+					
Water H2O with Glycole	+	+	+							+	+	+	+	+	+	
Water, H2O	+	+	+	+						+	+	+	+	+	+	
Water, Hot above 90°C H2O	+		+							+	+	+	+	+		